

WEST SYSTEM<sup>®</sup> brand 421 Fire Retardant is a hydrated alumina powder that forms a fire retardant mixture for coating in engine room or galley areas.

### MIX RATIO

Mix the WEST SYSTEM<sup>®</sup> resin and hardener first as per instructions, taking great care to mix thoroughly, then gradually stir in the additive at a rate of 1 to 1 by weight.

WEST SYSTEM <sup>®</sup> 105 Resin	1L/1.15 kg
WEST SYSTEM <sup>®</sup> 205 Hardener	200 ml/208 gm
421 Fire Retardant (dry bulk)	1.36 kg

421 Fire Retardant will greatly increase the viscosity of the epoxy mix, that will require trowelling or squeegeeing into place.

### PROPERTIES

WEST SYSTEM<sup>®</sup> 421 Fire Retardant

- Odourless, white crystalline powder
- Cures to an off-white colour

PACK SIZES	
Order Code	PACK
421 B	1 kg
421 C	5 kg

### STORAGE

WEST SYSTEM<sup>®</sup> 421 Fire Retardant will keep for 2 years if kept in original containers at room temperature (15°C to 32°C), and out of direct sunlight. Containers should be tightly sealed to prevent moisture absorption.

### HEALTH AND SAFETY

WEST SYSTEM<sup>®</sup> 421 Fire Retardant has moderate sensitising potential, and should be kept out of the eyes and off the skin. Good room ventilation is usually adequate for most applications, however, it is recommended that care should be taken to avoid inhalation.

- Use with good ventilation and adequate safety equipment including impervious gloves, safety glasses and dust masks
- Wash skin thoroughly after handling.
- If eye contact occurs, immediately flush with running water for at least 15 (fifteen) minutes and seek medical advice.
- If swallowed, DO NOT induce vomiting, give plenty of milk or water and contact a doctor or the Poisons Information Centre.

NOTE Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, express or implied, including any warranty or merchantability or fitness, nor is protection from law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special or consequential damages. 27/05/04

WEST SYSTEM is a registered trademark of Gougeon Brothers, Inc., USA



**ATL composites Pty Ltd**  
Tel (+61) 7 5563 1222  
Fax (+61) 7 5563 1585  
info@atlcomposites.com  
www.atlcomposites.com